

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C08K 9/02, 7/16, C08J 3/22</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/38244</b> <b>(43) International Publication Date:</b> 3 September 1998 (03.09.98)
<b>(21) International Application Number:</b> PCT/US98/03431 <b>(22) International Filing Date:</b> 27 February 1998 (27.02.98)  <b>(30) Priority Data:</b> 60/038,544 28 February 1997 (28.02.97) US  <b>(71) Applicant:</b> INTERNATIONAL PAPER COMPANY [US/US]; 1422 Long Meadow Road, Tuxedo, NY 10987 (US).  <b>(72) Inventors:</b> ALFONSO, Jorge; 8313 Woodland Road, Pasadena, MD 21122 (US). ELBON, Leonard, R.; 204 Juneberry Way #3B, Glen Burnie, MD 21061 (US). FRANZOI, Eric, A.; 2020 Poplar Ridge Road, Pasadena, MD 21122 (US). FINNERTY, Donald, Wayne; 85 Wileys Lane, Pasadena, MD 21122 (US).  <b>(74) Agent:</b> NEIMARK, Sheridan; Browdy and Neimark, P.L.L.C., Suite 300, 419 Seventh Street N.W., Washington, DC 20004 (US).		<b>(81) Designated States:</b> European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> PARTICLE FILLED RESINOUS PRODUCT OF IMPROVED APPEARANCE  <b>(57) Abstract</b>  Plastic surfacing material of the FOUNTAINHEAD® type having a bold and aesthetically pleasing appearance is achieved by the use of TFR pigments, the latter of which are manufactured by orienting reflective flake pigments in a plastic substrate and grinding the substrate to a particulate material.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**PARTICLE FILLED RESINOUS PRODUCT OF IMPROVED APPEARANCE**

The present invention relates to improvements in decorative products formed of particle filled resins, commonly available in the marketplace under the names of CORIAN™

5 (Dupont) and FOUNTAINHEAD® (International Paper).

Products of the general character of the CORIAN™ and FOUNTAINHEAD® have been long known and are commonly available such as for use as kitchen and bathroom surfaces. Broadly speaking, these materials are formed of  
10 particle filled resins, the most common resins being polyesters and acrylates, and the fillers ranging widely, often used to give particular visual effects to the product. Many prior patents directed to these types of products exist, bearing titles such as "Resinous Product Simulating Onyx" in U.S. patent  
15 3,396,067; "Filled Polymethylmethacrylate Article and Process for its Manufacture" in U.S. patent 3,827,933; "Process for the Production of Marbleized Reinforced Polyacrylic Compositions" in U.S. patent 3,663,493; "Thick, Cured Polymethylmethacrylate Article and Process for its Preparation" in U.S. patent Re.  
20 27,093; "Reinforced Resin Compositions" in U.S. patent 3,789,051; "Use of Alumina Trihydrate in a Polymethylmethacrylate Article" in U.S. patent 3,847,865, these being just a few examples of the many U.S. patents which exist in this field.

25 The aforementioned products have achieved remarkable commercial success, especially for kitchen and bathroom surfaces, and are normally available in a great variety of appearances. For example, the aforementioned FOUNTAINHEAD® product is a solid, non-porous surfacing material available in a  
30 variety of colors and patterns which run throughout its thickness, giving it a soft, deep translucent and natural feeling of warmth. Yet this material is tough and resists heat, stains, mildew and impact, and can be easily repaired if damaged. The FOUNTAINHEAD® product line includes soft,  
35 neutral solid colors and "granite-like" patterns, as well as grays, black and whites.

- 2 -

Commonly used pigments in these products are small particles of inorganic compounds, often metallic oxides, which are roughly spherical in shape. Other pigments are also sometimes used, as well as fillers and larger pieces of colored material to provide different visual effects. Alumina trihydrate (ATH) is often included for its fire-retardant properties.

Buttons have been made for many years by injection molding or the like, using pearlescent and iridescent pigments, and such pigments have been used in other fields as well, such as in the manufacture of bowling balls.

Commercially available pigments of this type, called by various names such as opalescent, pearlescent, iridescent, interference and thermochromatic pigments, are used to give the products in which they are used a sheen, reflectivity and three dimensional look, and it would be desirable to be able to provide such an appearance in surfacing materials of the type with which the present invention is concerned, as broadly described above. However, until the present time this has not been successful for a variety of reasons, including the fact that many of such pigments, here referred to simply as "pearlescent", become buried in the body of the product so that their light reflecting properties become lost.

In addition, these commonly available pearlescent pigments are shear sensitive so that their pearlescent effect is killed by the addition of common opacifiers used in these products, such as titanium dioxide and ATH.

It is, accordingly, an object of the present invention to overcome deficiencies in the prior art, such as indicated above. It is another object of the invention to provide a new "pearlescent" additive which, when used in the manufacture of aforementioned products of the FOUNTAINHEAD® type, produce new, bold and aesthetically pleasing appearances. It is a further object of the present invention to provide such a surfacing material of the FOUNTAINHEAD® type which incorporates such improved "pearlescent" particles, and which

- 3 -

consequently have such a new, bold and aesthetically pleasing appearance.

Yet another object of the present invention is to provide a method of making such improved pearlescent particles, hereinafter sometimes called translucent fire retardant particles (TFRs). And still a further object of the present invention is to provide a process using such TFR particles to produce a number of new, visually aesthetically pleasing patterns in the FOUNTAINHEAD®-type products.

These and other objects are achieved in accordance with the present invention by providing appropriate TFR particles each containing oriented pearlescent flakes. The TFR particles are then used in the manufacture of the final FOUNTAINHEAD®-type products.

A preferred process for making the TFR particles involves mixing conventional plastic, preferably polyester although acrylics and other polymers can also be used, together with conventional fillers, commonly used in the manufacture of FOUNTAINHEAD® and CORIAN™ type products, together with a particular commercially available pigment which comprises small mica flakes of about 5-50  $\mu\text{m}$  having angstrom thickness metal oxide coatings on their surfaces, often  $\text{TiO}_2$ , which coated mica flakes are commonly used to make pearlescent products including buttons and bowling balls. After the coated mica flakes, optional fillers, optional conventional pigments for color, and uncured plastic are mixed together to form the TFR composition, curing (preferably complete curing) of the plastic is carried out in such a way as to cause the mica flakes to become oriented in particular orientation patterns. One preferred way of accomplishing this orientation is to cast the mixture of flakes and plastic, with or without fillers and other pigments, onto a flat metal plate or belt and heat the mixture differentially, e.g. from the bottom through a metal conveyor belt, so as to cause the flakes to become oriented in generally oval patterns.

Regardless of how orientation of the flakes is carried out, the cured product, e.g. in solid ribbon form, is then ground to different particle sizes, to produce a granular TFR

- 4 -

product, which translucent fire retardant particles are themselves used as an additive in the manufacture of the final FOUNTAINHEAD® type products. A key factor in obtaining the desired final product is the nature of the TFRs which contain the coated mica flakes become locally oriented in the same direction, as use of the original coated mica flakes alone in the manufacture of the final product, without the intermediate manufacture of the TFRs will not give the desired results; one reason why flakes *per se* and alone do not produce a good final product is that in commercial production of the final product, the flakes do not orient in such a way as to give the desired appearance.

A wide variety of product appearances can be provided according to the present invention: for example, using appropriate brown pigments, products having the appearance of burl wood are made which cannot be made according to the prior art.

In the manufacture of the TFRs, it is desirable to grind the pearlescent flake-containing solidified ribbon to provide TFR particles of reasonably large size, desirably on the order of at least 50  $\mu\text{m}$  of minimum dimension. There is no limit on the maximum size of such TFRs, except it is preferred that they be no larger than 5 cm in their greatest dimension; their size is also limited by the thickness of the final product which is conventionally made in thicknesses of one-half and three-quarter inches. TFRs in any one final product can be provided in a variety of sizes simply by variable crushing of the cured ribbon.

In the manufacture of the final product, the TFRs in plural sizes, preferably at least two or three different sizes, are added to the conventional mix in amounts of up to 30-35% in mixes where ATH is an ingredient as is preferred, or in an amounts up to about 60% where the product is ATH-free. It is preferred that small quantities of the coated mica flake pigment also be added to the final mix, preferably in a quantity which is less than the quantity of the TFRs, e.g. up to 50% of the quantity of the TFRs, to provide a final product having a

- 5 -

somewhat enhanced appearance. In the manufacture of the final product, the TFRs become randomly reoriented to provide the final product, which has a somewhat pearlescent appearance. However, it is preferred that the composition of the final decorative product be passed through a die to orient parallel to the plane of the resultant product whatever raw coated flakes may be present in the composition.

The final product preferably contains about 50-60% ATH, including the ATH present in the TFRs, and about 15-20% TFRs, and also preferably about 1-5% additional conventional pigment, most preferably pigment of the coated mica type. The additional pigment, preferably of the coated mica type, gives a good background for the TFR particles.

In more detail, in the manufacture of the TFRs using the aforementioned coated mica flakes, the presently preferred method is to form a first mixture of pigments, hereinafter sometimes called a holomar pigment formulation, then mix the holomar pigment formulation with resin and optional filler, e.g. ATH, and then to continuously cast the composition on a heated belt so that there is a thermal gradient. When heat is applied upwardly from the heated belt, the coated mica flakes tend to orient in generally oval shaped patterns. When the cured ribbon is thereafter ground to different particle sizes to produce the different particle sized TFRs, and these TFRs are then used in the manufacture of the final product, the pigment alignment is such that the holomar pigments of the TFRs reflect light in many different planes which shift as the frame of reference of the viewer changes.

The composition for making the TFRs can vary widely, and typically contains 30-95% (preferably 30-50%) curable resin, preferably thermosetting polyester or thermosetting acrylic syrup; 0-65% (preferably 45-65%) ATH; 0.7-50% (preferably 6-10%) holomar pigment formulation as explained below; 0-40% (preferably 3-8%) methyl methacrylate monomer; and appropriate initiator and/or catalyst, e.g. 0.2-3.5% methyl ethyl ketone peroxide and 0.01-0.1% of a 12% cobalt octoate composition. The aforementioned holomar pigment formulation is formed of 15-100%

- 6 -

of the commercially available coated mica flakes, 0-20% black pigment, 0-20% of other standard colored pigments, 0-80% of a diluent which is preferably a thermoplastic (non-reactive) polyester, 0-80% of reactive resin which is preferably a  
5 thermosettable polyester, and 0-5% of a wetting agent.

In the most preferred method, the aforementioned TFR composition, preferably initially without the holomar pigment formulation and catalyst which are later metered in, is well mixed such as in a kneading continuous mixer, and the final  
10 mixture is cast onto the heated belt on which the mixture is cured to a solid. The resultant solid ribbon passes to a hammer mill where it is crushed and then conveyor fed to a granulator and then to a three-roll mill with adjustable rollers so that the maximum size of the TFR particles can be controlled. The  
15 TFR particles can either be separated to sizes such as by using screens and then remixed according to what is desired, or it can be used as is without classification, preferably after removal of fines.

Some non-limitative examples of formations are given below.

20 A preferred composition for the manufacture of the TFR particles consists of approximately 48% ATH, approximately 44% thermosettable polyester resin, approximately 7% of the holomar pigment formulation, and approximately 1% in total of methyl methacrylate monomer, catalyst and initiator. One holomar  
25 pigment formulation for producing a sapphire color consists of about 30% of coated mica flakes, about 70% of thermoplastic polyester as diluent, and less than 1% of black pigment. A similar holomar formulation, but without the black pigment, produces a bronze/copper color. An olive-colored holomar  
30 formulation is formed of approximately 33% of the coated mica flakes, 18% black pigment and 48.5% non-reactive polyester as a diluent.

FOUNTAINHEAD® sheet product is made according to standard practice and standard formulation, but to which is  
35 added, in three separate runs, respectively 15% of said TFR particles, 20% of said TFR particles and 25% of said TFR



- 7 -

particles, based on the total composition. The resultant FOUNTAINHEAD® sheet products contain respectively about 60%, 55% and 50% ATH, with the remainder in each case being predominantly the thermoset polyester with relatively minor amounts of other materials as indicated above. The TFRs can also be used in the manufacture of shaped goods.

Suitable exemplary and non-limitative pigment formulation examples, in addition to those set forth above, are set forth below:

10      Example 1 - Copper colored pigment for making TFRs

70% thermosettable polyester resin

30% copper colored coated flakes

(Mearlin Super Copper 9350Z)

15      Example 1A - Copper colored additional pigment

70% non-reactive polyester diluent

30% copper colored coated flakes

(Mearlin Super Copper 9350Z)

20      Example 2 - Bronze colored pigment for TFRs

70% thermosettable polyester resin

30% bronze colored coated flakes containing black pigment (Mearlin Super Bronze 9250Z)

25      Example 2A - Bronze colored additional pigment

70% non-reactive polyester as diluent

30% Bronze color coated flakes containing black pigment (Mearlin Super Bronze 9250Z).

30      Example 3 - Biege colored pigment for TFRs

66.01% thermosettable polyester resin

29.70% shiny metallic colored coated flakes (Mearlin Super Sparkle 9110S)

2.97% gold colored coated flakes

(Mearlin Sparkle Gold 9212P)

1.00% wetting agent

0.30% dark brown color coated flakes

(Mearlin Nu Antique Bronze 9240AB)

0.02% green pigment (Ferro Green 11-41057)

35

- 8 -

Example 3A-Biege colored additional pigment

66.01% non reactive polyester as diluent  
29.70% shiny metallic colored coated flakes  
(Mearlin Super Sparkle 9110S)  
5 2.97% gold colored coated flakes  
(Mearlin Sparkle Gold 9212P)  
1.00% wetting agent  
0.30% dark brown color coated flakes  
(Mearlin Nu Antique bronze 9240AB)  
10 0.02% green pigment (Ferro Green 11-41057)

Example 4 - Dark Green Pigment for TFRs

48.50% thermosettable polyester resin  
30.00% light sandy colored coated flakes with green  
hue (Mearlin Hi Lite Super Green 9830Z)  
15 18.00% black pigment (carbon black)  
3.50% gold colored coated flakes  
(Mearlin Sparkle Gold 9212P)

Example 4A - Dark Green Additional Pigment

48.50% non reactive polyester as diluent  
20 30.00% light sandy colored coated flakes with green  
hue (Mearlin Hi Lite Super Green 9830Z)  
18.00% black pigment (carbon black)  
3.50% gold colored coated flakes  
(Mearlin Sparkle Gold 9212P)

25 The following non-limitative example is for the  
manufacture of the TFRs:

Example 5

48.02% ATH  
44.14% thermosettable polyester resin  
30 6.67% TFR pigment, e.g. according to  
examples 1, 2, 3 or 4  
0.90% catalyst  
0.25% methymethacrylate monomer  
0.03% cobalt octoate solution (12%)

35 The foregoing description of the specific embodiments  
will so fully reveal the general nature of the invention that

- 9 -

others can, by applying current knowledge, readily modify and/or adapt for various applications such specific embodiments without undue experimentation and without departing from the generic concept, and, therefore, such adaptations and modifications should and are intended to be comprehended within the meaning and range of equivalents of the disclosed embodiments. For example, the surfacing materials of the present invention can be made using acrylic or acrylate polymers instead of polyester polymers. It is to be understood that the phraseology or terminology employed herein is for the purpose of description and not of limitation. The means, materials, and steps for carrying out various disclosed functions may take a variety of alternative forms without departing from the invention.

Thus the expressions "means to..." and "means for...", or any method step language, as may be found in the specification above and/or in the claims below, followed by a functional statement, are intended to define and cover whatever structural, physical, chemical or electrical element or structure, or whatever method step, which may now or in the future exist which carries out the recited function, whether or not precisely equivalent to the embodiment or embodiments disclosed in the specification above, i.e., other means or steps for carrying out the same function can be used; and it is intended that such expressions be given their broadest interpretation.

30

35

- 10 -

WHAT IS CLAIMED IS:

1. A "pearlescent" pigmenting additive for plastic products, termed "translucent fire retardant particles" (TFRs), in particulate form, comprising resin particles of different size containing oriented pearlescent reflective flakes.

2. The additive pigment of claim 1 wherein said plastic particles of at least two different sizes are formed from a ground sheet in which said flakes are oriented.

3. Filled plastic surfacing material of the FOUNTAINHEAD® type having a new, bold and aesthetically pleasing appearance, containing TFRs according to claim 1.

4. The surfacing material of claim 3 further containing at least one of ATH and up to 5% raw coated reflective flakes oriented substantially parallel to surfaces of said surfacing material.

5. Filled plastic surfacing material of the FOUNTAINHEAD® type having a new, bold and aesthetically pleasing appearance, containing TFRs according to claim 2.

6. The surfacing material of claim 5 further containing at least one ATH and up to 5% raw coated reflective flakes oriented substantially parallel to surfaces of said surfacing material.

7. A method of making TFRs according to claim 2, comprising mixing a binder resin and the aforementioned reflective flakes, solidifying the binder resin in such a way as to cause orientation of the flakes, and comminuting the resultant body.

8. A method of making TFRs according to claim 1, comprising mixing a binder resin and the aforementioned

- 11 -

reflective flakes, solidifying the binder resin in such a way as to cause orientation of the flakes, and comminuting the resultant body.

9. A method of making a filled surfacing material of the FOUNTAINHEAD®-type having a new bold and aesthetically pleasing appearance comprising adding TFRs according to claim 1 to a conventional plastic mix and then otherwise forming the resultant product in the conventional way.

10. A method according to claim 9, further comprising adding up to 5% of raw coated reflective flakes and orienting said flakes substantially parallel to opposite surfaces of said surfacing material.

11. A method of making a filled surfacing material of the FOUNTAINHEAD®-type having a new bold and aesthetically pleasing appearance comprising adding TFRs according to claim 2 to a conventional plastic mix and then otherwise forming the resultant product in the conventional way.

12. A method according to claim 11, further comprising adding up to 5% of raw coated reflective flakes and orienting said flakes substantially parallel to opposite surfaces of said surfacing material.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/03431

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08K9/02 C08K7/16 C08J3/22

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 417 515 A (HACHEY KATHLEEN A ET AL) 23 May 1995 see claims 1-14 ---	1-12
X	US 4 090 773 A (BAUER PETER ET AL) 23 May 1978 see claims 1-3 see example 1 ---	1-12
X	US 5 496 630 A (HAWRYLKO ROMAN B ET AL) 5 March 1996 see column 6 - column 7; example 1 see claim 1 ---	1-12
X	EP 0 723 997 A (TOPY IND) 31 July 1996 see examples 31,36 see claims 1,29 --- -/--	1-12

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "Z" document member of the same patent family

Date of the actual completion of the international search

24 June 1998

Date of mailing of the international search report

03/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Siemens, T

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/03431

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 2 168 068 A (ARMSTRONG WORLD IND INC) 11 June 1986 see page 3 - page 4; examples 1,2 -----	1-12

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Application No

PCT/US 98/03431

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5417515 A	23-05-1995	AU 683751 B	20-11-1997
		AU 2429595 A	18-12-1995
		BR 9507641 A	19-08-1997
		CA 2189022 A	30-11-1995
		EP 0760883 A	12-03-1997
		JP 10504076 T	14-04-1998
		WO 9532337 A	30-11-1995
		US 5571362 A	05-11-1996
		US 5750191 A	12-05-1998
US 4090773 A	23-05-1978	DE 2544245 A	14-04-1977
		AT 359720 B	25-11-1980
		CA 1085205 A	09-09-1980
		FR 2326549 A	29-04-1977
		NL 7610912 A	05-04-1977
US 5496630 A	05-03-1996	NONE	
EP 0723997 A	31-07-1996	JP 8199087 A	06-08-1996
		CN 1138069 A	18-12-1996
		JP 8259841 A	08-10-1996
		US 5741355 A	21-04-1998
GB 2168068 A	11-06-1986	US 4605584 A	12-08-1986
		AU 576912 B	08-09-1988
		AU 4905485 A	12-06-1986
		BE 903773 A	02-06-1986
		CA 1256287 A	27-06-1989
		DE 3542294 A	12-06-1986
		FR 2574085 A	06-06-1986
		JP 1710030 C	11-11-1992
		JP 3067863 B	24-10-1991
		JP 61133255 A	20-06-1986
		NL 8503252 A	01-07-1986
		SE 8505651 A	04-06-1986
		US 4699820 A	13-10-1987